

*

(2009/1/26 2008/9/15)

DMF

BMA

r_2, r_1

Synthesis Study of the copolymerization of Benzidine with some Vinyl Monomers

Ebtehag Z . Sulyman
Department of Chemistry
College of Education for Girls
Mosul University

ABSTRACT

The study includes the preparation of the acidic monomer, benzidine bis maleimic BMA, and the monomer was investigated by IR technique. Copolymerization of the acidic monomer benzidine bis maleamic BMA with styrene, methyl methacrylate in was accomplished DMF was studies. The copolymers were investigated by their colors, solubility and IR technique.

The relative monomer reactivity ratios in prepared copolymers were studied and azeotropic copolymerizations was not found at all monomer concentrations and the PBMA ratio was higher in copolymer in all cases. Thermal studies of the copolymers by using TGA, IGA technique, Indicate that the polybismaleimide possess higher thermal stability in comparison with other polymaleimides .As well as, thermal stability in was increased directly with increasing the molar ratios of acidic monomer benzidine bismaleamic acid BMA. The reactivity ratios study appeared that the type of copolymerization prefers to be alternate copolymer.

(Allcock *et al.*, 2003)

(Gaylord *et al.*, 1971,1971^{*})

(Jebrael,1983) (Gaylord *et al.*, 1972,1972^{*})

(Mohamed *et al.*, 1988)

(đ)

(Aliwi *et al.*, 1989)

(Mohamed *et al.*, 1997)

(Mohamed *et al.*, 1988, 1996)

-N

(0.5)

F_2^*

R

$4(N-RPM)^{**}$

.....

DMF (Oish *et al.*, 1989)

(OCH₃,CH₃, Cl, H)

N-RPM

(Saleh *et al.*,1997)

R

(-4)- N] -

(V) [

()

-N

TGA

DMF

(Sabaa *et al.*, 1986)

DTA

(A-Maadheedi *et al.*, 2003)

.

:

(BDH)

(Fluka)

%5

inhibitor

54

197

(DMF)

(THF)

(dM₂)

= F₂^{*}

- R- N =(N-RPM)^{**}

-1

UV. Visible double-beam spectrometer

(GBC Scientific equipment pty ltd (c) 1998)

1×1×3 cm⁻³ matched

.(Blank)

-2

Pye UNICAM SP 1100 Infra Red Spectrophotometer

-3

Electrothermal Melting point-Apparatus

(TGA)

-4

.(McCaffery, 1970)

(1° 5)

(IGA)

-5

TGA

, ° 300

0.98 () BMA

20

40

0.54

° 10

° (20-17)

12

(Malemic acid)

° 60

.....

\ . 24
 .° (205-200)

:


(M₁) BMA (M₂)
 DPB (30) DMF
 $\frac{M_2}{M_1} \left(\frac{M_2}{M_1 + M_2} = 0.66 \right)$
 / ([M₁]+[M₂]=0.66) 0.66
 C° 150 -100
 (60 C°) (Homo polymer)

(1)

.(5-1)


:1

Polymer	Color	Solvent	Precipitant
Poly - BMA		DMF	
Poly - ST			
Poly - MMA			
Copoly (BMA- ST)		DMF	
Copoly (BMA- MMT)		DMF	



(BMA)


:1



poly(BMA)


:2

.....




poly - ST

:3




Copoly (BMA- ST)

:4



Poly MMA

:5



Copoly (BMA- MMA)

:6

.....

(BMA)

DMF

MMT


ST

DMF


DPB

:

C 150-100




(dibenzoyl peroxide)





Benzoyl Radical


(R)



COPOLYMER



Copolymer (BMA- ST)



Copolymer (BMA- MMT)

.(1)

(7) (6)

(F₁)

(f₁)

(BMA)

$$f_1 = \frac{[M_1]}{[M_2]}$$

M₂

M₁

(f₁)

$$F_1 = \frac{dM_1}{dM_2}$$

M₁

(F₁)

M₂

.(0.88-0.75=F₁)

.(Jebrael, 1983; Hasan, 1989)

:

r₂,r₁

M₂

M₁(BMA)

(3) (2)

(KELEN-TUDOS, 1975; Kuo *et al.*, 1983)

-

:

$$\eta = \left(r_1 + \frac{r_2}{\alpha} \right) \xi - \frac{r_2}{\alpha}$$

:

.....

$$\eta = \frac{G}{\alpha + F} \text{ and } \xi = \frac{F}{\alpha + F}$$

$$\alpha = \sqrt{F_{\min} F_{\max}} \quad (\text{Symmetrization Parameter})$$

$$F = \frac{X^2}{Y} \quad G = \frac{X(Y-1)}{Y}$$

$$\begin{matrix} \cdot & M_2 & M_1 & =X \\ \cdot & M_2 & M_1 & =Y \end{matrix}$$

$$X = \frac{[M_1]}{[M_2]} \quad \text{-----} \quad Y = \frac{dM_1}{dM_2}$$

	(BMA- MMA)	α	3.00	(BMA-ST)	α
r_2, r_1	(9) (8)		intercept	slop	3.9284316
:	(3) (2)			-	
0.4152396= r_2	0.847889226 r_1		(BMA-ST)	0.4685385= r_2	0.98649 = r_1
		r_2		r_1	(BMA-MMA)
0.3520771= r_1r_2		(BMA-ST)	0.4622085= r_1r_2		r_1r_2
			1 >> r_1r_2		(BMA-MMA)
		(Elias, 1984)		r_1r_2	

:
()

(Thermo Gravimetric Analysis TGA)

(Isothermal Gravimetric Analysis IGA)

- .Initial Decomposition Temperature (IDT) -
- .Complete Decomposition Temperature (CDT) -
- .(%wt) 300 -

IDT TGA
 (4)

(BMA)

BMA

(CDT)

(BMA)
 %87-14 300

(IGA) (13) (12)
 300

BMA

% 95-25 ° 300

300 (4) (TGA)

.....

KELEN- - ST (PBMA) :2
TUDOS

BMA M ₁	ST M ₂	X=M ₁ /M ₂	dM ₁	dM ₂	Y=dM ₁ /dM	G=[X(Y- 1)/Y]	F=X ₂ /Y	η=[G /(a+F)]	ξ=[F/(a+F)]
0.1	0.9	0.111	0.90	0.1	9.0	0.085048	0.0028953	0.02832	0.000956
0.2	0.8	0.25	0.89	0.11	8.0909	0.1951212	0.0137196	0.0647443	0.0045523
0.3	0.7	0.428	0.88	0.12	7.3333	0.3407905	0.0376196	0.1121899	0.0123846
0.4	0.6	0.666	0.87	0.13	6.6923	0.5396285	0.0846391	0.1749405	0.0274388
0.5	0.5	1.0	0.86	0.14	6.1428	0.8372093	0.1627907	0.2647128	0.0514454
0.6	0.4	1.5	0.84	0.16	5.25	1.2758618	0.3362072	0.3824288	0.1007752
0.7	0.3	2.333	0.83	0.17	4.8823	2.0151	0.7424033	0.5384507	0.198375
0.8	0.2	4.0	0.82	0.18	4.5555	3.505617	1.9775303	0.7042884	0.3972914
0.9	0.1	9	0.81	0.19	4.2631	8	9	0.666666	0.75


KELEN- - MMA (PBMA) :3
TUDOS

BMA M ₁	MMA M ₂	X=M ₁ /M ₂	dM ₁	dM ₂	Y=dM ₁ /dM ₂	G=[X(Y- 1)/Y]	F=X ₂ /Y	η=[G /(a+F)]	ξ=[F/(a+F)]
0.1	0.9	0.111	0.84	0.16	5.25	0.074066	0.004114	0.018834	0.0010462
0.2	0.8	0.25	0.83	0.17	4.8823	0.1710477	0.019736	0.433233	0.009987
0.3	0.7	0.428	0.82	0.18	4.5555	0.30050	0.054845	0.761112	0.137688
0.4	0.6	0.666	0.81	0.19	4.2631	0.478517	0.12533	0.1180587	0.0309169
0.5	0.5	1.0	0.79	0.21	3.7619	0.734176	0.26582	0.1750434	0.0633772
0.6	0.4	1.5	0.78	0.22	3.5454	1.148143	0.52778	0.2576497	0.1184367
0.7	0.3	2.333	0.77	0.23	3.3478	1.8211054	1.1951024	0.3554416	0.2331907
0.8	0.2	4.0	0.76	0.24	3.1666	3.180714	3.277144	0.435382	0.4485815
0.9	0.1	9.0	0.75	0.25	3.0	7.2857	15.4285	0.376377	0.7970542


:4

BMA M₁ mole/L	ST M₂ mole/L	:		at 30°C (Wt%)
		IDT/C°	CDT/C°	
0.9	0.1	137	520	87
0.8	0.2	135	500	79
0.7	0.3	127	470	39
0.6	0.4	125	450	30
0.5	0.5	122	420	25
0.4	0.6	117	410	26
0.3	0.7	102	400	32
0.2	0.8	97	385	20
0.1	0.9	78	370	15
BMA M₁ mole/L	MMA M₂ mole/L	:		at 30°C (Wt%)
		IDT/C°	CDT/C°	
0.9	0.1	130	510	86
0.8	0.2	130	495	79
0.7	0.3	122	480	33
0.6	0.4	122	450	32
0.5	0.5	115	430	30
0.4	0.6	107	400	20
0.3	0.7	99	380	19
0.2	0.8	88	370	16
0.1	0.9	68	360	14


.....




ST (BMA) F_1 f_1 :6




MMA (BMA) F_1 f_1 :7



– MMA (BMA) ϵ η :8




– MMA (BMA) ϵ η :9




ST (BMA)

:10



MMA (BMA)


:11



ST (BMA)

:12

300



MMA (BMA)

:13

300

- Aliwi, S.M., and Bamford, C.H., 1989. Photoinitiation of Polymerization of Methyl Methacrylate by Hydroxy – Oxobis (8-Quinoloxp)-Vanadium(v)n-Butylamine ion – Pair Complex. *J. Photochem. and Photobiol.*, 47, 253p.
- Allcock, H.R.; Lamp, F.N., and Mark, I.E., 2003. *Contemporary Polymer Chemistry*. 3rd.Edn., Pearson Education, NI, 10p.
- Al-Maadheedi, A.M.; Mohamed, A.A., and Kalil, S.M., 2003. Free –Radical Copolymerization of Furan with Maleic Anhydride. *Raf. Jour. Sci.* Vol.14, No.1, pp.12-20.
- Ellias, H.G., 1984. *Macromolecules Synthesis, Materials and Technology*. Vol.2, Ed. Plenum Press. N.Y.
- Gaylord, N.G.; Stolka, M.; Takahashi, A., and Maiti, S., 1971. Conjuguated Diene-Maleic Through Radical Catalysed Polymerization. *J. Macromol. Sci. Chem.* A.5, 867p.
- Gaylord, N.G., and Maiti, S., 1971. Charge –Transfer Complex, Alternating Dien-dienophile Copolymers. *J. Polym. Sci.*, part B, 9, 359p.
- Gaylord, N.G.; Maiti, S., and Patnaik, B.K., 1972. Alternating Dien - dienophile Copolymers-Copolymerization of Cis and trans 1,3 –Pentadiene with Maleic Anhydride and Acrylonitrile. *J. Macromol. Sci. Chem.* A.6, 1435p. (C.A.44058q).
- Gaylord, N.G.; Maiti, S.; Patnaik, B.K., and Takahashi, A., 1972. Copolymerization of Furan and 2-Methyl Furan with Maleic Anhydride. *J. Macromol. Sci. Chem.* A.6, 1459p. (C.A.124963w).
- Hasan, M.H., 1989. M. Sc.Thesis, Mosul Univ.
- Jebrael, F.H., 1983. M. Sc., Mosul Univ.
- Kelen, T., and Tudos, F., 1975. Analysis of the Llinear Methods for Determination Copolymerization Reactivity Ratios, *J. Macromol. Sci. Chem.* A.9, pp.1-27.
- Kuo, J.F., and Chen, C.Y., 1983. A Method of Calculating Copolymerization. Reactivity Ratios, *J. Appl. Polym. Sci.* 26, pp.1117-1128.
- McCaffery, E.L., 1970. *Laboratory Preparation for Macromolecular Chemistry*. Mc Graw-HILL. N.Y. pp.263-290.
- Mohamed, A.A., 1986. Investigation of Charge Transfer Complexes Between N-Aryl Maleimides and Styrene. *Acta Polymerica*, 37, 8, pp.514-517.
- Mohamed, A.A.; Elsabee, M.Z., and Jabreal, F.H., 1986. Copolymerization of Styrene with N-Aryl Maleimides. 19, pp.32-37.
- Mohamed, A.A.; Al- Yamor, K.Y., and Ahmed, K.M., 1988. Copolymerization of Maleic Anhydride, N-2- Chlorophene Maleimide and N- α - Naphthyl Maleimide with Styrene. *Acta Polymerica*, 39, 7, pp.363-368.
- Mohamed, A.A., 1997. Interaction and Copolymer-2 at on of N- Aryl Maleimides. *Raf. Jour. Sci*, Vol.8, No. 2, pp.11-22.
- Mohamed, A.A., and Qasim, T.A., 1994. Differential Thermal Analysis of Polybis-Maleimide Copolymers. *MU'TAH J. Res. Stud.*, 9, 2, pp.117-137.
- Oishi, T.; Motiwak, M., and Fujimo, to M., 1989. Reactivities of α – Chlorophenyl Maleimides. *J. Macromol, Sci. Chem.*, A 26, 6, pp.841-896.

- Sabaa, M.; Mikhaeal, M.; Yassin, A., and Elsabee, M.Z., 1986. Copolymerization of Acrylonitrile with N-Substituted Maleimides. *Ang Matromol. Chem.*, 139, pp.95-112.
- Saleh, N.J., and Aliwi, S.M., 1997. Synthesis Chrruacteristion.Curing and Thermal Stability Study of Some New (Polyester -Polyether)IPN'S. *Iraq J. of Polymer*, 1, 1, pp.79- 92.