

The Electronic Properties of Dicyano Naphthalene Molecules Group

Z. Yousif Mijbil, A. Ibraheem Obaes, M. Kadhim Abed, Noor Amir Nama, Adil Jalil Najim, Huda Bukheet Hassan and Hamed Ibrahim Aboud
Babylon University –Iraq

Abstract

The electronic properties of cyanonaphthalene molecules group were investigated depending on the B3LYP density functional theory. The best geometry for the structures of the studied molecules was investigated by using 6-31G** basis set. Total energies, electronic states, energy gaps, ionization potentials and electron affinities were calculated. As a result, the total energy for naphthalene was decrease linearly with the number of side group added to the ring. The forbidden energy gap was reduced and 1,3dicyanonaphthalene molecule has the smallest value.

الخلاصة

تم في هذا البحث فحص الخواص الالكترونية لمجموعة جزيئات سيانونفتالين بالإعتماد على طريقة دالية الكثافة. حيث تم إيجاد التراكيب الهندسية المثلى للجزيئات قيد الدراسة باستخدام الدوال الأساسية من نوع 6-31G** إضافة الى حساب الطاقة الكلية، الحالات الالكترونية، فجوات الطاقة، جهود التأين و الالفات الالكترونية للجزيئات. لقد تم التوصل الى ان الطاقة الكلية و فجوة الطاقة لجزيئة النفثالين تتناقص مع زيادة عدد المجموعات الجانبية المضافة الى الحلقة و بشكل خطي و أن أدنى قيمة وجدت لدى الجزيئة (1,4,dicyano-naphthalene).

Introduction

Aromatic compounds are important in industry and play key roles in the biochemistry of all living things [1]. The organic semiconductor materials, such as, conjugated organic molecules have been widely used as active materials for optoelectronic devices such as light emitting diodes[2-5], field effect transistor[6-9], and photovoltaic and solar cells[10,11]. The organic thin film transistors are one type of the so called organic devices, in which they fabricated by using the organic semiconductors [12]. These materials have advantages of easy fabrication, mechanical flexibility and low cost. There are many organic materials show useful field effect transistor performance, which can be characterized by their carrier mobility and on/off current ratios [13, 14].

Many studies on cyclic oligomers have been reported both experimentally and theoretically [15, 16], in [17] the substituent effects of oligomers such as oligothiophene, oligopyrrole and oligofuran are discussed in terms of reorganization energy. Also, [18] studied the geometric and electronic properties for cyanothiophene oligomers as a prototype of an organic conducting polymer using ab initio and density functional theory, and they showed that the cyano group generally reduced the band gap with variation of the substitution position.

In present work, density functional theory has been performed to study the electronic properties of the dicyanoaromatic molecules to determine the effects of the substituent position.

Computational details

Our molecules under study have been shown in chart 1. The optimization of molecular geometries and analyses of vibration frequencies have been done by employing Gaussian 03[19] package of programs at the density functional theory level by using three parameters Lee-Yang-Parr (B3LYP) functional with 6-31G basis sets. The hybrid functional B3LYP has shown to be highly successful for the electronic properties calculation such as ionization potentials, electronic states and energy gaps [20-22].

According to B3LYP functional, the exchange correlation energy is given by [23, 24]:

$$E_{XC}^{B3LYP} = E_{XC}^{LDA} + a_o(E_X^{HF} - E_X^{LDA}) + a_x(E_X^{GGA} - E_X^{LDA}) + a_c(E_C^{GGA} - E_C^{LDA})$$

Where E represents energy, while superscripts LDA, HF, and GGA are localized density approximation, Hartree-Fock, and generalized gradient approximation respectively, and the subscripts X, C, and XC represent the exchange, correlation, and exchange-correlation respectively, while $a_o=0.20$, $a_x=0.27$ and $a_c=0.81$ are empirical parameters.




Chart 1: The structures of studied molecules

Results and discussion

Table (1) represents the results of the total energy and electronic states for the analyzed structures of the studied molecules.

Table (1): Total energy and electronic states for molecules

Structure	Energy (a.u)	Electronic States (eV)	
		HOMO	LUMO
Naphthalene	-385.8076808	-5.82512	-0.96187
1,monocyano naphthalene	-478.0192455	-6.37204	-1.90007
1,2dicyano-naphthalene	-570.2239636	-6.86263	-2.67365
1,3dicyano-naphthalene	-570.2268948	-6.9029	-2.56998
1,4dicyano-naphthalene	-570.2272784	-6.85774	-2.78113

It is clear that from table (1), the total energy for all new molecules depends on the number of side groups adding to the ring. The total energy is decreasing with the increase of the radicals number as a linear relationship, this indicates that the addition give the molecule more stability. On the other hand, the total energy for all dicyanonaphthalene molecules is approximately the same in

which this refer to that the total energy is independent on the position of the dicyano radical in the ring, as we see in figure (1).




Figure (1): Total energy as a function of radicals' number.

B3LYP functional, used in this study, is a high efficient method to calculate the electronic properties of the organic molecules under study, such as ionization potentials (IP), electron affinities (EA), electronic chemical potentials (k), hardness (η), electrophilicities (w) and energy gaps (E_g). Figure (2) declares that the ionization potential for the dicyanonaphthalene molecules group is less than that for the naphthalene molecule, but the 1,4dicyanonaphthalene molecule has the least value of ionization potential, this indicates that the naphthalene molecule needs high energy to become cation comparing with the others. Adding the radical to the ring leads to decreasing the ability of the electron affinity for the molecule, the electron affinity for 1,3dicyanonaphthalene molecule is the smallest, as we see in figure (3). The results in figure (3) mean that these cyanonaphthalene molecules group need small energy to become anion in comparing with naphthalene.

Figures (4) and (5) represent the behavior of chemical potential and hardness for the studied molecules as a function of side groups' number, respectively. It is obvious from these figures that the group molecules have chemical potential and hardness less than these for the original ring, adding the radicals give the molecule more softness.

The electrophilicity for studied molecules as a function of side groups' number is shown in figure (6). The substitution of the side groups reduced the population in the high occupied molecular orbitals, and this led to a decrease in the energy gap for the original ring, this effect of the side group was the largest in 1,4dicyanonaphthalene molecule in which it has energy gap of (4.076 eV), as shown in figure (7) [25].

Conclusions:

In order to elucidate the positional preference in cyano side groups on naphthalene molecule, we have estimated total energy of cyanonaphthalene molecules at the basis of B3LYP/6-31G**. The total energy for the naphthalene ring were reduced linearly with the number of adding side groups, and the origin of the reduction was attributed to the electron localization on the side group in the highest occupied molecular orbital. This ionization led the molecules have reduced energy.

The electronic chemical potential for cyanonaphthalene molecules are lower values comparing with the original ring. A hard molecule has a large energy gap and a soft molecule has a small energy gap. The cyanonaphthalene molecules are soft with small energy gaps. Therefore, the electron densities for these molecules are changing more easily than for naphthalene, thus these molecules may be more active compared with naphthalene.

The decreasing of the forbidden energy gap for the cyanonaphthalene molecules group compared with the original ring comes from the effect of the side group added to the ring, a small energy gap means small excitation energies of manifold of the excited states.




Figure (2): The ionization potential for studied molecules.




Figure (3): The electron affinity for studied molecules.




Figure (4): The chemical potential for studied molecules.




Figure (5): The hardness for studied molecules.




Figure (6): The electrophilicity for studied molecules.




Figure (7): The forbidden energy gap for studied molecules.

References:

1. K. J. Denniston, J. Topping and T. M. Dwyer, "General Organic and Biochemistry", 5th Edition, Towson University, 2007.
2. C. Tang, S. A. VanSlyke, Appl. Phys. Lett., 51, 913, 1987.
3. J. H. Burroughes, D. C. Bradley, A. R. Brown, R. N. Marks, K. Mackay, R. H. Friend, P. L. Burns, A. B. Holmes, Nature (London), 347, 539, 1990.
4. J. R. Sheats, H. Antoniadis, M. hueschen, W. Leonard, J. Miller, R. Moon, D. Roitman and A. Stocking, science, 273, 884, 1996.
5. R. H. Friend, R. W. Gymer, A. B. Holmes, J. H. Burroughes, R. N. Marks, C. Taliani, D. C. Bradley, D. A. Dos Santos, J. L. Bredas, M. Logdlund, W. R. Salaneck, Nature (London), 397, 121, 1999.
6. F. Garnier, R. Hajlaoui, A. Yassar, P. Srivastava, Science, 265, 1648, 1994.
7. G. Horowitz, D. Fichou, X. Z. Peng, Z. G. Xu, F. Gamier, Solid State Commun, 72, 381, 1989.
8. G. Horowitz, Adv. Mater, 10, 365, 1998.
9. H. E. Katz, A. J. Lovinger, J. Johnson, C. Kloc, T. Siegrist, W. Li, Y. Y. Lin, A. Dodabalapur, Nature (London), 404, 478, 2000.
10. G. Yu, J. Wang, J. Mc Elvain, A. Heeger, Adv. Mater, 10, 1431, 1998.
11. C. J. Brabec, N. S. Sariciftci, J. C. Hummelen, Adv. Funct. Mater, 11, 15, 2001.
12. H. E. Katz, J. Mater. Chem, 7, 369, 1997.
13. H. Klauk, D. J. Gundlach, M. Bonsel, C. C. Kuo, T. Jackson, Appl. Phys. Lett, 76, 1692, 2000.
14. T. W. Kelley, D. V. Muryes, P. F. Baude, T. P. Smith, T. P. Jones, Mater. Res. Soc. Symp. Proc, 771, 169, 2003.
15. M. D. Curtis, J. Cao, J. W. Kampf, J. Am. Chem. Soc, 126, 4318, 2004.
16. S. E. Koh, C. Risko, D. A. de Silva Filho, O. Kwon, A. Facchefti, J. L. Bredas, T. J. Marks, M. A. Ratner, Adv. Funct. Mater, 18, 332, 2008.
17. G. R. Hutchison, M. A. Ratner, T. J. Marks, J. Am. Chem. Soc, 127, 2339, 2005.
18. M. A. De Oliveira, H. F. Dos Santos, W. B. De Almeida, In. J. Quan. Chem, 90, 603, 2002.
19. M. J. Frisch and J. A. Pople, Gaussian 03, Inc. Pittsburgh PA, (2003).
20. J. Engelberts, R. Havenith, J. Van Lenthe, L. Jenneskens, P. Fowler, Inorg. Chem, 44, 52266, 2005.
21. J. C. Santos, W. Tiznado, R. Contreras, P. Fuentealba, J. Chem. Phys, 120, 1670, 2004.
22. J. C. Santos, J. Andres, A. Aizman, P. Fuentealba, J. Chem. Theory Comput, 1, 83, 2005.
23. H. Dorsett and A. White, " Overview of Molecular and Ab Initio Molecular Orbital Methods Suitable For Use With Energetic Materials", Aeronautical and Maritime Research Laboratory, Australia, 2000.
24. G. E. Scuseria and V. N. Staroverov, " Progress in the development of exchange- correlation functional ", Elsevier, Amsterdam, 2005.
25. A. J. Najim, "Density functional theory and semiempirical investigations for studying some aromatic molecules," M. Sc. Thesis, Babylon University, 2011.